

SHORT-ARC, ULTRA-HIGH-PRESSURE DISCHARGE LAMP  
AND METHOD OF MANUFACTURE

**Background of the Invention**

**Field of the Invention**

[0001] This invention concerns a short-arc, ultra-high-pressure discharge lamp into which is sealed mercury that has a mercury vapor pressure of at least 160 atmospheres when the lamp is lit, and a method of manufacturing such a lamp. More particularly, the invention is directed to a short-arc, ultra-high-pressure discharge lamp used as a back light in such equipment as liquid crystal display equipment, and a method of manufacturing such a lamp.

**Description of Related Art**

[0002] The ability to show images evenly and with adequate chromaticity on a rectangular screen is required for projection-type liquid crystal display equipment, and so metal halide lamps that incorporate mercury or a metal halide have been used as light sources for that application. In recent years, these metal halide lamps have become smaller and approached point light sources, and extremely small inter-electrode gaps have become practical.

[0003] In these circumstances, proposals have been made for lamps with unprecedentedly high mercury vapor pressure, such as 160 atmospheres, to replace metal halide lamps. These pressures are intended to suppress the spread of the arc and further increase light output as the mercury vapor increases.

[0004] In ultra-high-pressure lamps of this sort, the quartz glass that makes up the side tubes that extend from both sides of the luminescent tube must seal the metallic foil with sufficient tightness. In the manufacturing process to seal the tubes, the quartz glass is heated to a high temperature of, for example, 2,000° C, after which the thick quartz glass contracts slowly, or else the quartz glass is subjected to a pinch seal to increase the tightness of the portion involved.

00074231.060601

[0005] However, if the quartz glass is raised to too high a temperature, the tightness between the quartz glass and the metallic foil can be raised by the contraction or pinch seal, but there is the problem of cracking of the seal. In the stage where the temperature of the side tube drops at the conclusion of the sealing process, the difference in the indices of thermal expansion of the electrode and the quartz glass cause cracks where the two are in contact.

[0006] As shown in Figure 1, there is a proposal to resolve this problem by wrapping the electrode 2 with coil material 5. This eases the stress on the quartz glass from the thermal expansion of the electrode 2. This type of technology is described in, for example, published Japanese Patent Application H11-176385.

[0007] As shown in Figure 1, however, even when the electrode 2 is wrapped with the coil material 5, very small cracks K occur near the electrode 2 and the coil material 5.

[0008] These cracks K are extremely small, but in the event that the mercury vapor pressure in the luminescent tube 10 is around 160 atmospheres, such cracks sometimes lead to breakage of the side tube 11. Moreover, there has been demand in recent years for unusually high mercury vapor pressures of 300 atmospheres. With such high mercury vapor pressure, the cracks K are caused to grow longer when the lamp is lighted, and the breakage of the end tube 11 occurs to a marked extent.

### **Background of the Invention**

[0009] This invention is directed to resolving problems of the above indicated type. In particular, it is an object of this invention to form side tubes that have a sufficiently great resistance to pressure, and provide a short-arc ultra-high-pressure discharge lamp with such end tubes as well as a method for manufacturing such lamps.

[0010] In accordance with a first embodiment of the invention, a short-arc, ultra-high-pressure discharge lamp comprises a luminescent tube within which a pair of electrodes face each other and side tubes that extend from both sides of the luminescent tube and seal a portion of the electrodes, in which a small space is formed to enable the electrodes to expand and contract freely without compression along their axes that would be caused by a difference in the indices of expansion of the materials that make up the electrodes and the side tubes.

[0011] The method of manufacture of a short-arc, ultra-high-pressure discharge lamp in accordance with the invention comprises the following processes:

007457.000001

[0012] 1) heating the electrodes and metallic foil to a temperature higher than the softening point of the side tubes, and then sealing the electrodes and metallic foil with the side tubes;

[0013] 2) cooling the sealed side tubes to fix the metallic foil in the end tubes;

[0014] 3) re-heating the portion of the side tube in which the electrode is sealed, softening the side tube and bringing the side tube into contact with the electrode while in a viscous, fluid state, so that the electrode can rub against the portion of the side tube that is in a viscous, fluid state; and

[0015] 4) vibrating the re-heated side tube and electrode such that the temperature of the portion of the side tube in which the electrode is sealed reaches a temperature region between the side tube's softening point and its annealing point when the side tube softens and contacts the electrode while in a viscous, fluid state, and the electrode can rub against the portion of the side tube that is in a viscous, fluid state.

#### **Brief Description of the Drawings**

[0016] Figure 1 is an explanatory cross-sectional view of a portion of a conventional short-arc, ultra-high-pressure discharge lamp;

[0017] Figure 2 shows a short-arc, ultra-high-pressure discharge lamp in accordance with the present invention;

[0018] Figure 3 is an explanatory cross-sectional view of a portion of the short-arc, ultra-high-pressure discharge lamp of Figure 2;

[0019] Figure 4 is a transverse cross section taken along line A-A of Figure 3;

[0020] Figures 5(a)-5(b) depicts steps of a method of manufacturing the short-arc, ultra-high-pressure discharge lamp of this invention; and

[0021] Figure 6 another embodiment of a short-arc, ultra-high-pressure discharge lamp in accordance with the invention.

#### **Detailed Description of the Invention**

[0022] Figure 2 shows a short-arc, ultra-high-pressure lamp 1 in accordance with the present invention in which the discharge lamp 1 has a luminescent portion 10 made of quartz glass nearly at its center, with side tubes 11 on opposite sides. The side tubes 11 are tightly sealed quartz glass.

[0024] Mercury is contained in the luminescent tube 10 as the luminous substance, and a rare gas, such as argon or xenon, is also included as a start-up gas. The amount of mercury contained is calculated so as to provide a vapor pressure, when the lamp is burning stably, of at least 150 atmospheres, preferably 200 atmospheres or more, and better yet 300 atmospheres or more. For example, to produce a mercury vapor pressure of at least 150 atmospheres, the amount of mercury would be at least 0.15 mg/mm<sup>3</sup>.

**[0026]** Within the side tube 11, as shown in Figures 3 & 4, the electrode 2 is attached only where it is welded to the metallic foil 3; in the rest of that region, the gap B is present between the electrode and the quartz glass. In specific terms, the electrode sides 2a and the electrode end 2b do not contact the side tube 11 (quartz glass).

### Sealing Process

[0029] Next, the electrode 2 is positioned so that its tip is exposed within the luminescent tube 10, and the stem of the electrode 2 and the metallic foil 3 are located in the side tube 11.

**[0030]** Next, as shown at C in the figure, the side tube 11a that encompasses the electrode 2 and metallic foil 3 is heated to a temperature above the softening point of the side

tube 11a. To be specific, when the side tube is made of quartz glass, the softening point is  $1,680^{\circ}\text{C}$ , and so the side tube 11a can be heated using a gas burner to a temperature of about  $2,000^{\circ}\text{C}$ .

[0031] In this sealing process, the side tube 11a is already closed on one side. Therefore, the pressure within the glass bulb can be reduced to 100 Torr, for example, through the open end of the other side tube 11b. Then, when the side tube 11a is heated, that portion will be reduced in diameter, and the electrode 2 and metallic foil 3 will be sealed by that means.

[0032] Now, rather than using negative pressure in the glass bulb in this way, it is possible to use a pincer to seal the side tube 11 after heating it.

#### Cooling Process

[0033] Next, Figure 5(b) shows the cooling process during which the heated side tube 11 is cooled either by forced cooling or natural cooling, and continues until the temperature at which the metallic foil 3 is fixed in the side tube 11, for example  $1,200^{\circ}\text{C}$ , is reached. This cooling process results in fusing of parts of the electrode 2 to the side tube 11, but that does not mean that the full length of the electrode 2 is fused to the material that makes up the side tube 11. That is because the material that makes up the electrode 2, such as tungsten, and the material that makes up the side tube, such as quartz glass, have different indices of thermal expansion, and so part of the fused portions of the electrode 2 and the side tube 11 (the portion fused in the sealing process) separate. It is when this separation occurs that the small cracks K (Fig. 1) develop.

#### Heating Process

[0034] Next, Figure 5(c) shows the heating process, which follows the cooling process, in which the portion indicated by **D** in the figure is re-heated. The heating is performed using a gas burner, for example, and continues until the material that makes up the side tube 11, such as quartz glass, is in a viscous, fluid state and is again in contact with the electrode 2, so that the materials that make up the electrode 2 and the side tube 11 are free to rub against each other.

[0035] This heating process is a matter of re-heating just the region of the side tube 11 indicated by **D** in the figure, and so the region where the metallic foil 3 is already

00874231-060601  
T0990-1227260



•

—

will not push against the inside of the side tube 11, the side tube 11 will not break, even though the mercury vapor pressure in the luminescent tube is extremely high.

[0048] A numerical example of the short-arc, ultra-high-pressure discharge lamp of this invention is described next.

Cathode diameter:	0.8 mm
Anode diameter:	1.8 mm
Side tube outer diameter:	6.0 mm
Total lamp length:	65.0 mm
Side tube length:	25.0 mm
Capacity of luminescent tube:	0.08 cc
Inter-electrode gap:	2.0 mm
Rated voltage:	200 V
Rated current:	2.5 A
Mercury content:	0.15 mg/mm <sup>3</sup>
Rare gas:	Argon at 100 Torr

[0049] Other implementations of this invention are explained below.

[0050] Figure 6, like Figure 3, shows a detail of the luminescent tube 10 and the side tube 11. In this implementation, that part of the stem of the electrode 2 that is located within the side tube 11 is made with a ridged surface 20. This ridged portion 20 has a depth of 1.0 to 100  $\mu$ m (the ridges are exaggerated in the drawing).

[0051] By using this ridged portion 20 it is possible, in the vibrating process, to form gap **B** more certainly. The reason for this is not entirely clear, but it is thought that the quartz glass that enters between the ridges during the heating process is thrown out by the vibrations applied from the outside, and that the gap **B** is formed by that action.

09874231-000001